



ARLON

▶ DPF 510GTR / MTR Vinyl Film

Digital Print Pressure-Sensitive Vinyl Film

DPF 510GTR / MTR is a 3.2-mil (80 micron) calendered film with a tinted, solvent-based pressure-sensitive removable adhesive. The two-sided polycoated liner provides excellent lay-flat properties. DPF 510 is available in a white gloss (DPF 510GTR) and white matte finish (DPF 510MTR). DPF 510 is rated for outdoor durability up to 3 years (unprinted). Printed durability is dependent on the ink system used.

APPLICATIONS & FEATURES

- Low tack adhesive is removable up to one year
- Short-term promotional and display graphics, including windows, decals, tradeshow and POP displays
- Excellent printability on Eco-Solvent, Solvent and Latex print systems
- Ideal for interior and exterior applications on flat surfaces

PERFORMANCE & PHYSICAL DATA

PROPERTY	TEST METHODS	TYPICAL VALUE	
SURFACE FINISH	Gloss Meter 60° Reflection	70 to 90 Gloss Units (Gloss) Up to 30 Gloss Units (Matte)	
THICKNESS	Micrometer, Federal Bench Type	3.2-mil (80 micron)	
TENSILE STRENGTH	Tensile Tester with 2-in (51 mm) jaw separation; crosshead speed of 12 in/min. (5.1 mm/s), web direction	≥ 10.0 lb/in	≥ 1.8 kg/cm
ELONGATION	Instron Tensile Tester as above	≥ 200%	
SHELF LIFE (IN BOX)	Ideal Storage Temperature 70°F (21°C) and 50% relative humidity	1 year from factory shipment	
APPLICATION TEMPERATURE RANGE	On clean, dry substrate	50°F to 90°F	10°C to 32°C
SERVICE TEMPERATURE RANGE	On clean, dry substrate	-20°F to 150°F	-29°C to 65°C
DIMENSIONAL STABILITY	158°F (70°C), 48 hours	≥ 40-mil	≥ 1.00mm
PEEL ADHESION	PSTC-1, 15 min, 70°F (21°C)	≥ 0.50 lb/in	≥ 0.09 kg/cm
LINER RELEASE	TLMI Release at 90°, 300 in/min (760 cm/min)	110 g/2 in	21.7 g/cm




Standard Terms & Conditions Apply






TERMS & CONDITIONS

The following is made in lieu of all warranties expressed or implied:

All statements, technical information and recommendations published by Arlon relating to Arlon products are based on tests believed to be reliable and within the accuracy of the equipment used to obtain the specific values. Their accuracy or completeness is not guaranteed and Arlon makes no warranty with regard thereto. Seller's and manufacturer's only responsibility shall be to replace any quantity of the product proved defective. Seller and manufacturer shall not be liable for injury, loss or damage, direct or consequential, arising out of use or the inability to use the product. Nor shall seller or manufacturer be liable for any costs or expenses incurred in the processing or printing on the product. Before using, user shall determine the suitability of the product for its intended use. User assumes all risk and liability of every nature in connection therewith. No statements or recommendations other than those contained in the technical information published by Arlon shall have force or effect unless contained in an agreement manually signed by the officers of seller and manufacturer.

October 2016

USA:  200 Boysenberry Lane, Placentia, CA 92870, USA
EUROPE:  North Sea Building, Gevers Deynootweg 93, 4th Floor, 2586BK Den Haag, The Netherlands
UK:  P6 Parklands, Heywood Distribution Park, Heywood, Lancashire OL102TT, UK

 800 232 7161/+1 714 985 6300  800 329 2756
 +31 70 354 4311  +31 70 355 7721
 +44 161 884 0592  +31 70 355 7721

arlon.com