



▶ DPF 510 ULTRA TACK Vinyl Film

Digital Print Pressure-Sensitive Ultra Tack Vinyl Film

DPF 510 Ultra Tack is a 100 microns monomeric film with a clear or tinted, solvent-based, pressure-sensitive, ultra tack adhesive. The two-sided polycoated liner provides excellent lay-flat properties. The high tack adhesive provides superior adhesion for multi-purpose signage applications. DPF 510 Ultra Tack is available in a white gloss finish (DPF 510G-UT or DPF 510GT-UT) and white matte finish (DPF 510M-UT or DPF 510MT-UT). DPF 510 Ultra Tack is rated for outdoor durability up to 3 years (unprinted). Printed durability is dependent on the ink system used.

APPLICATIONS & FEATURES

- Short-term promotional and display graphics
- Barricade graphics, tradeshow signage or construction graphics
- Ideal for interior and exterior applications on flat surfaces
- Excellent printability on Eco-Solvent, Solvent, and Latex print systems

PERFORMANCE & PHYSICAL DATA

PROPERTY	TEST METHODS	TYPICAL VALUE
SURFACE FINISH	Gloss Meter 60° Reflection	70 to 90 Gloss Units (Gloss) Up to 30 Gloss Units (Matte)
THICKNESS	Micrometer, Federal Bench Type	100 microns
TENSILE STRENGTH	Tensile Tester with 51 mm jaw separation; crosshead speed of 12 in/min. 5.1 mm/s, web direction	≥ 1.8 kg/cm
ELONGATION	Instron Tensile Tester as above	≥ 150%
SHELF LIFE (IN BOX)	Ideal Storage Temperature 21°C and 50% relative humidity	1 year from factory shipment
APPLICATION TEMPERATURE RANGE	On clean, dry substrate	10°C to 32°C
SERVICE TEMPERATURE RANGE	On clean, dry substrate	-29°C to 65°C
DIMENSIONAL STABILITY	70°C, 48 hours	≥ 1.27mm
PEEL ADHESION	PSTC-1, 15 min, 21°C	≥21 N/25mm
LINER RELEASE	TLMI Release at 90°, 760 cm/min	7.0 g/cm

Standard Terms & Conditions Apply





TERMS & CONDITIONS

The following is made in lieu of all warranties expressed or implied:

All statements, technical information and recommendations published by Arlon relating to Arlon products are based on tests believed to be reliable and within the accuracy of the equipment used to obtain the specific values. Their accuracy or completeness is not guaranteed and Arlon makes no warranty with regard thereto. Seller's and manufacturer's only responsibility shall be to replace any quantity of the product proved defective. Seller and manufacturer shall not be liable for injury, loss or damage, direct or consequential, arising out of use or the inability to use the product. Nor shall seller or manufacturer be liable for any costs or expenses incurred in the processing or printing on the product. Before using, user shall determine the suitability of the product for its intended use. User assumes all risk and liability of every nature in connection therewith. No statements or recommendations other than those contained in the technical information published by Arlon shall have force or effect unless contained in an agreement manually signed by the officers of seller and manufacturer.

September 2018

USA:  200 Boysenberry Lane, Placentia, CA 92870, USA
EUROPE:  North Sea Building, Gevers Deynootweg 93, 4th Floor, 2586BK Den Haag, The Netherlands

 +1 714 985 6300  800 329 2756
 +31 70 354 4311  +31 70 355 7721

arlon.com