

WHITE PAPER CAD

80 g/m²

For use in thermal and piezo inkjet printers.
Water base and latex inks



TEPEDE D.O.O.
Vodovodna 20a, 10000 Zagreb, Hrvatska
T: +385 1 364 3641
F: +385 1 364 3686
E: prodaja@tepede.hr

2017 Data-sheet

Material description

White bond paper for everyday plotting.

Produces crisp line resolution and high-contrast colour print.

Both sides printable.

This selected paper has very good dry time and accepts the Ink very well

White paper CAD provides sharply contrasted black lines.

Qualifications

- Cad paper
- Opacity ISO 2471
- Quick drying
- Brilliant colours and excellent sharp line
- Archival 100 years
- BfR Food Certificate
- EMAS, EU Ecolabel
- FSC ChainofCustody
- PEFC ChainofCustody
- ISO 14001,ISO 9001,OHSAS 18001,ISO 9706

Indoor

White bond paper, specially developer for technical drawings and presentations.

Small characters from 1 mm are very sharp and fillings are colourfull.

Archival 100 years. ISO 9706 standard.

Outdoor

Specifications

Quality	ECF	Inkjet bond paper
Weight		80 g/m ²
Print side		White
Reverse side		White
Whiteness	96%	30% UV light elrepho ISO
CIE Whiteness	164%	White
Opacity		ISO 2471
Archival		100 years , ISO 9706 standard

Applications

- CAD
- GIS
- B/W + Colour inkjet printing
- B/W + Colour laser printing
- Offset preprinting

Compatibility

HP, EPSON, CANON, MUTOH

- ☞ WB dye
- ☞ WB pigment
- ☞ Laser Dry toner
- ☞ Latex

WHITE PAPER CAD

80 g/m²

For use in thermal and piezo inkjet printers.
Water base and latex inks



TEPEDE D.O.O.
Vodovodna 20a, 10000 Zagreb, Hrvatska
T: +385 1 364 3641
F: +385 1 364 3686
E: prodaja@tepede.hr

2017 Data-sheet

Guidelines

Printing

Always choose the right media for the right job.
There are different kinds of inks with different kind of properties.

Light stability

The light stability of a plot depends on various factors such as dye, pigment, latex, laser dry toner and media coating but the most important factor is direct sunlight. Direct sunlight and UV cause visible image deterioration on unprotected media within few weeks or longer.

Mechanical resistance

To protect the print against scratches and damage, it is recommended that media should be handled and used in a clean environment.

Water resistance

When the plot is completely dry, White paper cad shows high resistance to fingerprints, however contact with wet hands is not recommended.

Trouble shooting

Check that the media compatible with your printer and ink.
Choose the right print mode. Check the media setting (if this exists) coated paper, film, etc.
Perform cartridge alignment procedure if necessary.
If required clean the cartridges.

Color calibrations

As with all inkjet media , the product should be calibrated to the printer , to get the best result.

Loading instructions

The rate which ink consumed over a given area varies between different printers and printer set-ups. White paper cad has excellent ink absorption capacity. When loading the media use the right set-up (mode) that gives the highest quality output.

Printer setting and ink quantity

For optimum results, select the highest print quality.
Avoid 3 colour composite black , use single colour black only.

Shelf life and environment aspects

The shelf life of TEPEDE media is 1 year under normal conditions (10-25% at a relative humidity of 30-75%). Higher humidity and/or temperature can affect the product performance.
Always store the media in a dark place.

Ecology

The media and the final plots can be handled and disposed of as inkjet paper media. For the treatment of ink or ink residue, please refer to your printed manual or supplier.

Help available

If there are questions about media, just ask the TEPEDE sales department. They will inform you properly about our media program.

Note

Specifications subject to change without notice.